

FRAISE À LAMER 3/4  
FRÄSTICHEL 3/4  
COUNTERBORE ENDMILL 3/4


21013-4

Version du  
12.06.2020



E25  
UF

angle  
vif



Compatibilité outil / matière  
Werkzeug / Werkstoffverträglichkeit  
Tool / Material compatibility

● 1/3  
● 2/3  
● 3/3

E2  
Groupe Vc [m/min]



ESHOP / EZI CUT

|                                                                            |                                |     |     |   |
|----------------------------------------------------------------------------|--------------------------------|-----|-----|---|
| ACIERS ALLIÉS ET NON ALLIÉS<br>UNLEGIERTE STÄHLE<br>NON-ALLOYED STEELS     | Rm < 450 N/mm <sup>2</sup>     | 1a  |     |   |
|                                                                            | Rm 450 - 700 N/mm <sup>2</sup> | 1b  |     |   |
|                                                                            | Rm 700 - 900 N/mm <sup>2</sup> | 1c  |     |   |
|                                                                            | Rm < 1200 N/mm <sup>2</sup>    | 1d  |     |   |
| ACIERS INOX<br>ROSTFREIE STÄHLE<br>STAINLESS STEELS                        | Rm < 650 N/mm <sup>2</sup>     | 2a  | 30  | ● |
|                                                                            | Rm 650 - 950 N/mm <sup>2</sup> | 2b  | 20  | ● |
|                                                                            | Rm > 950 N/mm <sup>2</sup>     | 2c  | 10  | ● |
| ACIERS TREMPÉS GEHÄRTETE<br>STÄHLE HARDENED STEELS                         | 44 - 56 HRC                    | 3a  |     |   |
|                                                                            | 57 - 67 HRC                    | 3b  |     |   |
| MATÉRIAUX EXOTIQUES<br>EXOTISCHE WERKSTOFFE<br>EXOTIC MATERIALS            | < 32 HRC                       | 4a  |     |   |
|                                                                            | > 32 HRC                       | 4b  |     |   |
| GRAPHITE                                                                   |                                | 5   |     |   |
| FONTES GUSS CAST IRON                                                      | < 32 HRC                       | 6a  |     |   |
|                                                                            | > 32 HRC                       | 6b  |     |   |
| TITANE TITAN                                                               | Rm < 800 N/mm <sup>2</sup>     | 7a  |     |   |
|                                                                            | 800 < Rm N/mm <sup>2</sup>     | 7b  |     |   |
| ALLIAGES NICKEL<br>NICKEL<br>NICKEL ALLOYS                                 | Rm < 1000 N/mm <sup>2</sup>    | 8a  |     |   |
|                                                                            | 1000 < Rm N/mm <sup>2</sup>    | 8b  |     |   |
| CUIVRE, LAITON, BRONZE<br>KUPFER, MESSING, BRONZE<br>COPPER, BRASS, BRONZE | Rm < 850 N/mm <sup>2</sup>     | 9a  | 320 | ● |
|                                                                            | 850 < Rm N/mm <sup>2</sup>     | 9b  | 200 | ● |
| ALUMINIUM                                                                  | Si < 0.5%                      | 10a | 300 | ● |
|                                                                            | 0.5% < Si < 5%                 | 10b | 250 | ● |
|                                                                            | Si > 5%                        | 10c |     |   |
| MATIÈRES SYNTHÉTIQUES<br>KUNSTSTOFFE<br>SYNTHETIC MATERIALS                | Thermoplast                    | 11a |     |   |
|                                                                            | Duraplast                      | 11b |     |   |
| MATIÈRES COMPOSITES<br>FASERVERST. MATERIALEN<br>COMPOSITE MATERIALS       | Fibre de verre                 | 12a |     |   |
|                                                                            | Fibre de carbone               | 12b |     |   |
| MÉTAUX PRÉCIEUX<br>EDELMETALLE<br>PRECIOUS MATERIALS                       | Or • Gold                      | 13a | 320 | ● |
|                                                                            | Platine                        | 13b |     |   |



|              |      |
|--------------|------|
| D (h10)      | 4    |
| d (h6)       | 6    |
| L            | 57   |
| l1           | 5    |
| l3           |      |
| d3           |      |
| R            |      |
| e            |      |
| Z            | 1    |
| Chanfrein    |      |
| K            |      |
| w° collision | 6.4° |