


<p>CARBIDE TOOL MATERIAL E25 UF</p>	<p>CUTTING ANGLES $\lambda=30^{\circ}\text{--}35^{\circ}$ $\gamma=8^{\circ}$</p>	<p>ACUTE ANGLE PRECISION TOOL</p>	<p>DUAL DIRECTION HELICAL DRILL BIT</p>	<p>8xD LENGTH L3 CUTTING TOOL</p>	<p>EXTRA LONG PRECISION DRILL BITS</p>	<p>ADJUSTABLE ANGLE ICON</p>	<p>VARIABLE HELIX DRILL BIT</p>
-------------------------------------	--	-----------------------------------	---	-----------------------------------	--	------------------------------	---------------------------------

MATERIAL COMPATIBILITY

●●● Excellent (3/3) ●● Good (2/3) ● Possible (1/3) ○○○ Not recommended

MATERIAL	SPECIFICATION	GRP	21038D-0.6
Alloyed and non-alloyed steels <small>Non-alloyed steels</small>	Rm < 450 N/mm ²	1a	○○○
	Rm 450–700 N/mm ²	1b	○○○
	Rm 700–900 N/mm ²	1c	○○○
	Rm > 1200 N/mm ²	1d	○○○
Stainless steels <small>Stainless steels</small>	Rm < 650 N/mm ²	2a	○○○
	Rm 650–950 N/mm ²	2b	○○○
	Rm > 950 N/mm ²	2c	○○○
Hardened steels <small>Hardened steels</small>	44–56 HRC	3a	○○○
	57–67 HRC	3b	○○○
Exotic materials <small>Special alloys</small>	< 32 HRC	4a	○○○
	> 32 HRC	4b	○○○
Graphite <small>Industrial graphite</small>		5	●●●
Cast iron <small>Grey / nodular cast iron</small>	< 32 HRC	6a	○○○
	> 32 HRC	6b	○○○
Titanium <small>Titanium alloys</small>	Rm < 600 N/mm ²	7a	○○○
	600 < Rm N/mm ²	7b	○○○
Nickel alloys <small>Inconel, Hastelloy</small>	Rm < 1000 N/mm ²	8a	○○○
	Rm > 1000 N/mm ²	8b	○○○
Copper, brass, bronze <small>Copper-based</small>	Rm < 850 N/mm ²	9a	●●○
	Rm > 850 N/mm ²	9b	●●○
Aluminum <small>Aluminum alloys</small>	Si < 0.5%	10a	●○○
	0.5% < Si < 5%	10b	●●○
	Si > 5%	10c	●●●
Synthetic materials <small>Engineering plastics</small>	Thermoplastic	11a	○○○
	Thermoset	11b	○○○
Composite materials <small>Reinforced composites</small>	Glass fiber / GFK	12a	●●●
	Carbon fiber / KFK	12b	●●●
Precious metals <small>Gold, platinum, silver</small>	Gold	13a	●○○
	Platinum	13b	●●●

TECHNICAL DRAWING



DIMENSIONS

NOMINAL DIMENSIONS	
D (0 / -0.01)	0.6 mm
d (h5)	3 mm
L	38 mm
l1	3 mm
l3	–
d3	–
R	–
e	–
Z	3
Chamfer K	–
w° collision	8.6°

