FRAISE TORIQUE MD E2 · TORIC ENDMILL MD E2 · TORISCHE FRÄSER HM E2

21372-10-R1 Version 04.11.2026

SWISS MADE

E2 — SUBMICRON GRAIN GRADE HIGH-SPEED MACHINING OF ABRASIVE MATERIALS

λ=32°-38° Y=10° — VARIABLE HELIX ANGLES 32° - 38° AND CUTTING ANGLE 10°

CORNER RADIUS SHAPE

SIDE AND CENTER CUT

l1 2.2xD — CUTTING EDGE LENGTH 2.2XD

FITTING LENGTH STANDARD

IRREGULAR TOOTHING

λ2 λ1 — VARIABLE HELIX ANGLES

MATERIAL COMPATIBILITY

●●● Excellent (3/3) ●●○ Good (2/3) ●○○ Possible (1/3) ○○○ Not recommended

Product material compatibility

CATEGORY	MATERIAL	SPECIFICATION	GRP	21372-10-R1
	Alloyed and non-alloyed steels Non-alloyed steels	Rm < 450 N/mm²	1a	●○○ 1/3
		Rm 450–700 N/mm²	1b	○○○ 0/3
		Rm 700–900 N/mm²	1c	○○○ 0/3
		Rm > 1200 N/mm²	1d	○○○ 0/3
	Stainless steels Stainless steels	Rm < 650 N/mm²	2a	○○○ 0/3
		Rm 650–950 N/mm²	2b	○○○ 0/3
		Rm > 950 N/mm²	2c	○○○ 0/3
	Hardened steels Hardened steels	44–56 HRC	3a	○○○ 0/3
		57–67 HRC	3b	○○○ 0/3
	Exotic materials Special alloys	< 32 HRC	4a	○○○ 0/3
		> 32 HRC	4b	○○○ 0/3
	Graphite Industrial graphite		5	●○○ 1/3
	Cast iron Grey / nodular cast iron	< 32 HRC	6a	○○○ 0/3
		> 32 HRC	6b	○○○ 0/3
	Titanium Titanium alloys	Rm < 600 N/mm²	7a	●○○ 1/3
		600 < Rm N/mm²	7b	●○○ 1/3
	Nickel alloys Inconel, Hastelloy	Rm < 1000 N/mm²	8a	○○○ 0/3
		Rm > 1000 N/mm²	8b	○○○ 0/3
	Copper, brass, bronze Copper-based	Rm < 850 N/mm²	9a	●●● 3/3
		Rm > 850 N/mm²	9b	●●● 3/3
	Aluminum Aluminum alloys	Si < 0.5%	10a	●●○ 2/3
		0.5% < Si < 5%	10b	●●○ 2/3
		Si > 5%	10c	○○○ 0/3
	Synthetic materials Engineering plastics	Thermoplastic	11a	●●○ 2/3
		Thermoset	11b	●●○ 2/3
	Composite materials Reinforced composites	Glass fiber / GFK	12a	●○○ 1/3
		Carbon fiber / KFK	12b	●○○ 1/3
	Precious metals Gold, platinum, silver	Gold	13a	●●○ 2/3
		Platinum	13b	○○○ 0/3

TECHNICAL DRAWING



21372

DIMENSIONS

NOMINAL DIMENSIONS	
D (h10)	10 mm
d (h6)	10 mm
L	72 mm
l1	22 mm
l3	–
d3	–
R	1 mm
e	–
Z	3
Chamfer K	-
w° collision angle	-

E-SHOP / EZI CUT
eskenazi.ch/eshop/21372-10-R1

© 2026 Eskenazi SA — Carouge, Genève
All rights reserved