

FRAISE-MULTI-USAGE-MD-E25UF-+-EZI-ALPHA-POUR-MICRO-MACHINE · MULTI-USE-ENDMILL-SC-E25UF-+-EZI-ALPHA-FOR-MICRO-MACHINE · FRÄSER-MULTI-VERWENDUNG-HM-E25UF-+-EZI-ALPHA-FÜR-MIKROMASCHINE



SWISS MADE

23750A-90-0.6

Version du 06.08.2026

0.6
Ø D (MM)

28
L (MM)


2
Z

COMPATIBILITÉ MATIÈRE

●●● Excellent (3/3) ●●○ Bon (2/3) ●○○ Possible (1/3) ○○○ Non recommandé

MATIÈRE	SPÉCIFICATION	GRP	23750A-90-0.6
Aciers alliés et non alliés Aciers non alliés	Rm < 450 N/mm²	1a	○○○
	Rm 450–700 N/mm²	1b	○○○
	Rm 700–900 N/mm²	1c	○○○
	Rm > 1200 N/mm²	1d	○○○
Aciers Inox Aciers inoxydables	Rm < 650 N/mm²	2a	○○○
	Rm 650–950 N/mm²	2b	○○○
	Rm > 950 N/mm²	2c	○○○
Aciers trempés Aciers durs	44–56 HRC	3a	○○○
	57–67 HRC	3b	○○○
Matériaux exotiques Alliages spéciaux	< 32 HRC	4a	○○○
	> 32 HRC	4b	○○○
Graphite Graphite industriel		5	○○○
Fontes Fonte grise / nodulaire	< 32 HRC	6a	○○○
	> 32 HRC	6b	○○○
Titane Alliages titane	Rm < 600 N/mm²	7a	○○○
	600 < Rm N/mm²	7b	○○○
Alliages Nickel Inconel, Hastelloy	Rm < 1000 N/mm²	8a	○○○
	Rm > 1000 N/mm²	8b	○○○
Cuivre, laiton, bronze Cuivreux	Rm < 850 N/mm²	9a	○○○
	Rm > 850 N/mm²	9b	○○○
Aluminium Alliages aluminium	Si < 0.5%	10a	○○○
	0.5% < Si < 5%	10b	○○○
	Si > 5%	10c	○○○
Matières synthétiques Plastiques techniques	Thermoplastique	11a	○○○
	Thermodurcissable	11b	○○○
Matières composites Composites renforcés	Fibre de verre / GFK	12a	○○○
	Fibre de carbone / KFK	12b	○○○
Métaux précieux Or, platine, argent	Or	13a	○○○
	Platine	13b	○○○

DESSIN TECHNIQUE



DIMENSIONS

DIMENSIONS NOMINALES	
D (0 / -0.01)	0.6 mm
d (h5)	3 mm
L	28 mm
l1	1.2 mm
l3	–
d3	–
R	0.06 mm
e	–
Z	2
Chanfrein K	–
w° collision	10.9°



E-SHOP / EZI CUT
eskenazi.ch/eshop/23750A-90-0.6